



VERSEIDAG SEEMEE US, INC.
4 ASPEN DRIVE
RANDOLPH, NJ 07830
ATTN: GARLAND DREW

May 22, 2008

IDENTIFICATION SUBMITTED BY CLIENT

DESCRIPTION : NIGHT DROP 2 SIDE 10oz.
COLORS : WHITE
FIBER CONTENT : POLYESTER
END USE : BANNERS/SIGNS

FIRE RESISTANCE – (City of New York)

EVALUATION OF TEST RESULTS

The fabric sample submitted **DOES** meet the requirements for fire resistance in accordance with Rules for Test of Fire-Resistive, Flameproofed Materials as specified by the City of New York Board of Standards and Appeals under Calenda No. 294-40-SR

TEST RESULTS

		Flashing	Duration of Flame (second)	Duration of Glow (Second)
1	WARP/LENGTH	0.0	0.0	0.0
2	WARP/LENGTH	0.0	0.0	0.0
3	WARP/LENGTH	0.0	0.0	0.0
4	FILLING/WIDTH	0.0	0.0	0.0
5	FILLING/WIDTH	0.0	0.0	0.0
6	FILLING/WIDTH	0.0	0.0	0.0

Requirement

No flashing shall occur at any time on the length of the specimen. (Flashing due to fuzz or bad edges may be disregarded)

Average continuation afterflame shall not exceed three seconds

Average continuation of glow at the edge of the charred area shall not exceed 20 seconds. (Glow confined to the charred area may be disregarded)



Report No.: 144763

VERSEIDAG SEEMEE US, INC.
4 ASPEN DRIVE
RANDOLPH, NJ 07830
ATTN: GARLAND DREW

May 22, 2008

IDENTIFICATION SUBMITTED BY CLIENT

DESCRIPTION : NIGHT DROP 2 SIDE 10oz.
COLORS : WHITE
FIBER CONTENT : POLYESTER
END USE : BANNERS/SIGNS

NFPA 701 – STANDARD METHODS OF FIRE FOR FLAME RESISTANT TEXTILES AND FILMS 2004 EDITION – TEST METHOD #1

CONCLUSION

The item submitted for testing **DOES** pass the flame resistance requirements when tested in accordance with the procedures outlined in the National Fire Protection Association Standard 701, Test Method 1 small scale test.

TEST RESULTS

Specimen Configuration: Single Layer

State of Sample: As Received

Specimen Direction: LENGTH DIRECTION

SPECIMEN #	AFTERFLAME TIME	BURNING OF DRIPPINGS	WEIGHT BEFORE EXPOSURE	WEIGHT AFTER EXPOSURE	% WEIGHT LOSS
	(SECONDS)	(SECONDS)	(GRAMS)	(GRAMS)	
Test 1	0	0	19.2	16.5	14.06
Test 2	0	0	19.1	16.2	15.18
Test 3	0	0	19.2	15.6	18.75
Test 4	0	0	19	15.3	19.47
Test 5	0	0	19.1	16.3	14.66
Test 6	0	0	19.1	14.2	25.65
Test 7	0	0	18.9	15.8	16.40
Test 8	0	0	18.8	16.2	13.83
Test 9	0	0	19	16.4	13.68
Test 10	0	0	18.7	16.8	10.16
Average:	0	0			16.19
Std. Dev:					4.26

AVERAGE PERCENT WEIGHT LOSS FOR TEN SPECIMENS: 16.2

FAILURE CRITERIA:

Afterflame (seconds)	Mean Flaming Drip (seconds)	Weight Loss (percent)	
		Mean	Individual Specimen
None	Exceeds 2.0	exceeds 40%	exceeds mean + 3 SD

Retest Provision: Where the percent weight loss of any individual specimen exceeds the mean value plus three standard deviations, the test shall be repeated on another sample of 10 specimens.

**IF YOU NEED ASSISTANCE IN INTERPRETING THESE TESTS RESULTS
OR IF YOU HAVE ANY QUESTIONS, PLEASE FEEL FREE TO CALL:
CUSTOMER SERVICE DEPT.**

INTERTEK LABTEST

Eduardo Palomo
Senior Client Manager

AZ