

VERSEIDAG SEEMEE US, INC.
 4 ASPEN DRIVE
 RANDOLPH, NJ 07830
 ATTN: GARLAND DREW

MAY 31, 2007

IDENTIFICATION SUBMITTED BY CLIENT

DESCRIPTION : 12 OZ POLYESTER LAMINATE T. FLEX
 COLORS : WHITE

TEST RESULTS

NFPA 701 – STANDARD METHODS OF FIRE FOR FLAME RESISTANT TEXTILES AND FILMS 1999 EDITION – TEST METHOD #1

THE ITEM SUBMITTED FOR TESTING **DOES** PASS THE FLAME RESISTANCE REQUIREMENTS WHEN TESTED IN ACCORDANCE WITH THE PROCEDURES OUTLINED IN THE NATIONAL FIRE PROTECTION ASSOCIATION STANDARD 701, TEST METHOD 1 SMALL SCALE TEST.

STATE OF SAMPLE: AS RECEIVED

SPECIMEN #	AFTERFLAME TIME (SECONDS)	BURNING OF DRIPPINGS (SECONDS)	WEIGHT BEFORE EXPOSURE (GRAMS)	WEIGHT AFTER EXPOSURE (GRAMS)	% WEIGHT LOSS
Test 1	0	0	24.3	15.3	37.04
Test 2	0	0	24.3	16	34.16
Test 3	0	0	24.2	15.7	35.12
Test 4	0	0	24.3	15.5	36.21
Test 5	0	0	24.2	15.6	35.54
Test 6	0	0	24.2	15.4	36.36
Test 7	0	0	24.2	15.9	34.30
Test 8	0	0	24.1	15.5	35.68
Test 9	0	0	24.3	15.6	35.80
Test 10	0	0	24.2	15.5	35.95
Average:	0	0			35.62
Std. Dev:					0.89
AVERAGE PERCENT WEIGHT LOSS FOR TEN SPECIMENS:				35.6	

RETEST CRITERIA: Where the percent weight loss of any individual specimen exceeds the mean value plus three standard deviations, the test shall be repeated on another sample of 10 specimens. The mean percent weight loss and standard deviation for the second set of 10 specimens shall be calculated.

-continued-

PERFORMANCE CRITERIA

**Burning of
Drippings:**

7-1.1 Where fragments or residues of specimens that fall to the floor of the test chamber continue to burn for more than an average of 2 seconds Per specimen for the sample of 10 specimens, the material shall be recorded as failing Test 1

**Average Percent
Weight:**

7-1.2 where the average weight loss of the 10 specimens in a sample is greater than 40 percent, the material shall be recorded as failing this test.

-continued-

FIRE RESISTANCE – CITY OF NEW YORK

THE FABRIC SAMPLE SUBMITTED **DOES** MEET THE REQUIREMENTS WHEN TESTED, IN ACCORDANCE WITH RULES FOR TESTS OF FIRE-RESISTIVE, FLAMEPROOFED MATERIALS AS SPECIFIED BY THE CITY OF NEW YORK BOARD OF STANDARDS AND APPEALS UNDER CALENDAR NO. 294-40-SR

	<u>FLASHING</u>
1 WARP/LENGTH	NO
2 WARP/LENGTH	NO
3 WARP/LENGTH	NO
4 FILLING/WIDTH	NO
5 FILLING/WIDTH	NO
6 FILLING/WIDTH	NO
Average:	NO


REQUIREMENTS:

- NO FLASHING SHALL OCCUR AT ANY TIME ON THE LENGTH OF THE SPECIMEN. (FLASHING DUE TO FUZZ OR BAD EDGES MAY BE DISREGARDED)
- AVERAGES CONTINUATION AFTERFLAME SHALL NOT EXCEED THREE SECONDS
- AVERAGE CONTINUATION OF GLOW AT THE EDGE OF THE CHARRED AREA SHALL NOT EXCEED 20 SECONDS. (GLOW CONFINED TO THE CHARRED AREA MAY BE DISREGARDED)

**IF YOU NEED ASSISTANCE IN INTERPRETING THESE TESTS RESULTS
OR IF YOU HAVE ANY QUESTIONS, PLEASE FEEL FREE TO CALL:
CUSTOMER SERVICE DEPT.**

INTERTEK LABTEST

MK



Sanjeev Gandhi
Technical Director